

LABORATORY :- MOXLEY INDUSTRIAL CENTRE, WESTERN WAY,
ADDRESS WEDNESBURY, WEST MIDLANDS, WS10 7BG
TEL: 0121 505 4050 FAX: 0121 505 1115
www.rotechlabs.co.uk info@rotechlabs.co.uk

REGISTERED :- DARLSTON P.O. BOX 10, WEDNESBURY,
OFFICE WEST MIDLANDS, ENGLAND, WS10 8JD
TEL: 0121 526 3131 FAX: 0121 526 2869

Test Report

Our Ref: RDS/EAL Number 55252 Issue 1 Date 25/01/2006 Page 1 of 1

A/C No: M114

Tested For:-

T I MIDWOOD & COMPANY LIMITED
Green Lane
Wardle
Nantwich
Cheshire
CW5 6BJ

SALT SPRAY TESTING OF TIMCO WINDOW SCREWS

INTRODUCTION

Finished samples were submitted to the laboratory for Salt Spray Corrosion Resistance Testing in accordance with the relevant specification.

RELEVANT INFORMATION

Description: 20 off. **TIMCO WINDOW SCREWS**
Finish: Delta Coating
Specification: Salt Spray Test in accordance with ASTM.B117-03 /
BS.7479: 1991
Test Duration: 504 Hours Exposure
Submitted By: Peter Owen
Customer's Order No: 3599
Test Completion Date: 24/01/2006

RESULTS

Salt Spray Test (ASTM B117-03 / BS 7479: 1991 / DIN.50.021-SS)

The screws were exposed to a neutral 5% Salt Spray for a test period of 504 hours.

Examination after the test period revealed no evidence of red ferrous corrosion.

CONCLUSION

The finish applied to the screw samples tested, **withstood** 504 hours Salt Spray Test without breakdown.

End of Report

REPORT COMPILED BY



E A Love

Laboratory Technician

REPORT APPROVED BY



R D Smith

Chief Chemist

TESTS MARKED "NOT UKAS ACCREDITED" IN THIS REPORT/CERTIFICATE ARE NOT INCLUDED IN THE UKAS ACCREDITATION SCHEDULE FOR OUR LABORATORY.
TESTS MARKED 'SC' HAVE BEEN SUBCONTRACTED.
OPINIONS AND INTERPRETATIONS EXPRESSED HEREIN ARE OUTSIDE THE SCOPE OF UKAS ACCREDITATION.
THIS TEST REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL, WITHOUT WRITTEN APPROVAL OF THE LABORATORY.
RESULTS IN THIS REPORT RELATE ONLY TO THE ITEMS TESTED.