

Our Ref: GBW/RDS Number 62529 Issue 1 Date 20/03/2007 Page 1 of 2

A/C No: M114

Tested For:-

T I MIDWOOD & COMPANY LIMITED
Green Lane
Wardle
Nantwich
Cheshire
CW5 6BJ

SALT SPRAY TESTING OF TIMCO DRYWALL SCREWS

INTRODUCTION

Finished samples were submitted to the laboratory for Salt Spray Corrosion Resistance Testing in accordance with the relevant specification.

RELEVANT INFORMATION

Description:	20 Off. Timco Drywall Screws
Finish:	Black Finish
Specification:	Salt Spray Test in accordance with ASTM.B117-03
Test Duration:	60 Hours Exposure
Submitted By:	Peter Owen
Customer's Order No:	3768
Sample Receipt Date:	12/03/2007

RESULTS

Salt Spray Test (ASTM.B117-03 / BS.EN ISO 9227:2006 / DIN.50.021-SS)

The screws were exposed to a neutral 5% Salt Spray for a test period of 60 hours.

Examination every 24 hours revealed the following observations:-


24 – 60 Hours

No evidence of red ferrous corrosion.

REPORT COMPILED BY


G B Withers

REPORT APPROVED BY


R D Smith
Chief Chemist

Assistant Corrosion Chemist

CONCLUSION

The finish applied to the Timco Drywall Screw samples tested, **withstood** 60 hours Salt Spray Test without the formation of red ferrous corrosion.

End of Report